

SINCE



1952

PAINTS FOR INDUSTRY

HIGH SHEEN COLD GALVANIZING COMPOUND

A heavy duty, industrial grade spray coating that provides long lasting galvanic rust and corrosion protection for steel and other ferrous metals.

Formulated with high purity zinc pigments to prevent the formation and spread of rust, this coating dries to a bright metallic finish.

- ✓ Brilliant metallic finish
- ✓ Self healing cathodic barrier protection
- ✓ Outstanding corrosion and salt spray resistance
- ✓ 97% pure zinc
- ✓ MIR compliant

Revised May 2024

DIRECTIONS FOR USE

Apply High Sheen Cold Galvanizing Compound for long term anti-corrosion protection on metal structures and equipment. May be used for maintenance and restoration of worn or damaged galvanized surfaces.

Application: Shake vigorously for at least 30 seconds after marble begins rattling, and intermittently during application. Hold can 8-10 inches from the surface and spray with even strokes. Overlapping with several light coats will result in a better finish than a single heavy coat. After painting is complete, hold the can upside down and spray a short burst of gas to clear the nozzle. Do not insert pins or objects into the spray valve. Dispose of empty cans in accordance with all applicable regulations.

TECHNICAL DATA

Vehicle	Fast dry alkyd
Finish	Silver (High Gloss)
MIR	< 1.25
Heat Resistance	400 °F intermittent, 250 °F continuous
Pencil Hardness	B-HB
Impact Resistance	500g 1/2" x 50cm
Net Weight	11 oz.
Coverage	15 sq. ft.
Shelf Life	2 years
Dry to Touch	15 minutes

ADDITIONAL INFORMATION

Warning: The removal of old paint may release lead dust. Lead is toxic and can cause serious illness and brain damage, especially in children and pregnant women. Before removing old paint, ensure the use of proper protective equipment including a NIOSH approved respirator. For more information, call the National Lead Information Center at 1-800-424-LEAD. This product is intended for professional industrial use only. Thoroughly review the product label and Safety Data Sheet before using. Product information, including the SDS and a copy of this PDS is available online at www.pfiinc.net or by request. This product is free of lead and chrome.

Coating performance is dependent on adequate surface preparation and proper application. The information contained in this bulletin is correct to the best of our knowledge. The recommendations and suggestions herein are made without guarantee or representation as to the end result, since the conditions of use are not known and beyond our control. Such information is subject to change and pertains only to the product offered for sale at the time of publication. The user is encouraged to test the complete coating system for adhesion and compatibility prior to full-scale production.

Warranty and limitation of Seller's liability: PFI, Inc. warrants only that the products represented herein meet the formulation standards of PFI, Inc. This warranty shall be in lieu of any other warranty, expressed or implied, including but not limited to any implied warranty of merchantability or fitness for a particular purpose. There are no warranties that extend beyond the description on the face hereof. The buyer's sole and exclusive remedy against PFI, Inc. shall be for replacement of the product in the event a defective condition of the product should be found to exist, and the exclusive remedy shall not have failed its essential purpose so long as PFI, Inc. is willing to provide comparable replacement product to the buyer. No other remedy (including but not limited to incidental or consequential damages for lost profits, lost sales, injury to persons or property, environmental injuries, or any other incidental or consequential loss) shall be available to the buyer.



9215 Santa Fe Springs Road
Santa Fe Springs, CA 90670
562-946-6666 | info@pfiinc.net