



1952

## PAINTS FOR INDUSTRY

# AQUALIZE® ACRYLIC PRIMER

Fast drying, waterborne acrylic primer offering excellent corrosion protection for steel and fabricated metal products. Ideal for use on structural steel, ornamental iron, machinery, and equipment.

- √ Military grade
- ✓ Meets MIL-P-28577B, A-A-50557, & SSPC-Paint #15 performance specifications
- ✓ Superior flash rust & early moisture resistance
- √ Superior coverage and hiding
- √ Fast drying with low odor
- ✓ Low VOC

#### RECOMMENDED USES

For interior or exterior application to all properly prepared ferrous and non-ferrous metal surfaces, including structural steel, piping, tank exteriors, machinery and equipment, utility trailers, wrought iron, racking, handrails, and joists.

#### RECOMMENDED SYSTEM

1 coat Aqualize® Acrylic Primer 1 coat Aqua-Clad® Acrylic Enamel

#### SURFACE PREPARATION

Surface should be clean, dry, and free of all contaminants such as oil, rust, loose paint, mill scale, and any other detrimental matter to ensure proper adhesion. Ultra-Bond® Metal Cleaner is the recommended cleaning solution for all steel surfaces. The use of Ultra-Bond® will significantly improve adhesion on nonferrous metal surfaces such as aluminum and galvanized steel.

SSPC-SP2 Hand Tool Cleaning is the minimum recommended level of surface preparation. For best possible performance, use commercial blast cleaning per SSPC-SP6/NACE 3.

Warning! The removal of old paint may release lead dust. Lead is toxic and can cause serious illness and brain damage, especially in children and pregnant women. Before removing old paint, ensure the use of proper protective equipment, including a NIOSH approved respirator. For more information, call the National Lead Information Center at 1-800-424-LEAD.

#### CLEAN UP

Equipment, hoses, and spills can be cleaned with water. Flush equipment with acetone or mineral spirits after cleaning to prevent rusting.

#### TECHNICAL DATA

Finish Flat (0 - 10 units @ 60°)  Color Full range available  Volume Solids† 31 - 41%  Weight Solids† 38 - 52%  Weight per Gallon† 11 lbs	Vehicle	Acrylic
Volume Solids†         31 - 41%           Weight Solids †         38 - 52%           Weight per Gallon†         11 lbs	Finish	Flat (0 - 10 units @ 60°)
Weight Solids † 38 - 52%  Weight per Gallon † 11 lbs	Color	Full range available
Weight per Gallon <sup>†</sup> 11 lbs	Volume Solids <sup>†</sup>	31 - 41%
	Weight Solids †	38 - 52%
Viscosity † 70 75 KII	Weight per Gallon <sup>†</sup>	11 lbs
Viscosity 70 - 75 NO	Viscosity †	70 - 75 KU
VOC Less than 275 g/L (2.3 lbs/gal)	VOC	Less than 275 g/L (2.3 lbs/gal)
Shelf Life 6 months unopened	Shelf Life	6 months unopened
Recommended DFT 2.0 - 3.0 mils	Recommended DFT	2.0 - 3.0 mils
Coverage 300 - 400 ft / gal (theoretical)	Coverage	300 - 400 ft / gal (theoretical)
Packaging 1 gallon, 5 gallon, and 55 gallon containers	Packaging	
Application Airless or conventional spray	Application	Airless or conventional spray
Drying Time* @ 76°F, 50% RH	Drying Time*	@ 76°F, 50% RH
15 minutes to touch		15 minutes to touch
30 minutes to handle		30 minutes to handle
12 hours to topcoat		12 hours to topcoat

<sup>†</sup> May vary by color.

### **APPLICATION**

Temperature	40 F - 120 F
Relative Humidity	85% maximum
Recommended Reducer	Water
Airless Spray	
Pressure	1,800 - 2,200 psi
Hose	0.25" ID
Tip	.015"017"
Filter	60 mesh
Reduction	Not Recommended

40°E 120°E

#### Conventional / HVLP

Spray Gun Binks 95 or similar

Fluid Nozzle 63C
Air Nozzle 63PB
Atomization Pressure 50 PSI
Fluid Pressure 15 - 20 PSI

Reduction As needed up to 10% by vol.

Brush (touch up only)

Material Nylon/Polyester

#### ADDITIONAL INFORMATION

Coating performance is dependent upon adequate surface preparation and proper application. The information and recommendations contained in this product bulletin are based upon tests conducted by or on behalf of PFI, Inc. and are correct to the best of our knowledge. Such information is subject to change and pertains to the product offered for sale at the time of publication. All information and recommendations herein are made without guarantee or representation as to the end result, since the conditions of use, including variations in customer handling and methods of application, are not known and beyond our control. The user is encouraged to test the complete coating system for adhesion and compatibility prior to full-scale production.

This product is intended for professional industrial use only. Thoroughly review the product label and Safety Data Sheet before using. Product information, including the SDS and a copy of this PDS is available online at <a href="www.pfiinc.net">www.pfiinc.net</a> or by request. This product is free of lead and chrome.

Warranty and limitation of Seller's liability: PFI, Inc. warrants only that the products represented herein meet the formulation standards of PFI, Inc. This warranty shall be in lieu of any other warranty, expressed or implied, including but not limited to any implied warranty of merchantability or fitness for a particular purpose. There are no warranties that extend beyond the description on the face hereof. The buyer's sole and exclusive remedy against PFI, Inc. shall be for replacement of the product in the event a defective condition of the product should be found to exist, and the exclusive remedy shall not have failed its essential purpose so long as PFI, Inc. is willing to provide comparable replacement product to the buyer. No other remedy (including but not limited to incidental or consequential damages for lost profits, lost sales, injury to persons or property, environmental injuries, or any other incidental or consequential loss) shall be available to the buyer.



9215 Santa Fe Springs Road Santa Fe Springs, CA 90670 562-946-6666 info@pfiinc.net

<sup>\*</sup> Dry time varies by temperature, humidity, and film thickness.